

TECHNICAL SHEET



Article: **B0317 DAISY**
Norm: **EN ISO 20345:2011**
Safety Class: **S3 SRC**

Footwear height: **Mod. A, H 92 mm (< 105 mm, Ref. EN 20345-5.2.2)**

Width: **9**

Construction: **STROBEL; INJECTED BIDENSITY SOLE**

Cleaning and maintenance: Use only soft brushes and water. Do not use substances like alcohol, thinners, gasoline, oil or any other chemicals. Keep the footwear, dry and clean, in a proper place at room temperature.

Suggested fields: **light Industry, services**

Entire footwear: components				
Component	Description	Value	Norm Requirements	EN ISO 20345
Steel toe-cap	Impact resistance(200 J)			
	• Free height after impact	14mm	≥ 14 mm	5.3.2.3
Sole (SRC)	Compression resistance (15 kN)			
	• Free height after compression	14,5mm	≥ 14 mm	5.3.2.4
Sole (SRC)	Slip resistance			
	• SRA – Sole (entire sole)	0,47	≥ 0,32	5.3.5.4
	• SRA – Heel (Angle of 7°)	0,35	≥ 0,28	5.3.5.4
	• SRB – Sole (entire sole)	0,22	≥ 0,18	5.3.5.4
Fresh'n Flex (P)	Puncture resistance			
		No perforation	≥ 1100 N	6.2.1.1.2
Footbed (A)	Antistatic properties			
		• Electrical resistance	dry 6,5 x 10 ⁸ Ω Humid 2,47 x 10 ⁸ Ω	≥ 10 ⁵ Ω , ≤ 10 ⁹ Ω ≥ 10 ⁵ Ω , ≤ 10 ⁹ Ω
Sole/Upper	Thermal insulation			
		Heat (HI)	N/A	≤ 22°C
Cold (CI)	Insole temperature decrease			
			N/A	≤ 10°C
Heel (E)	Shock-absorption in the heel region	24 J	≥ 20 J	6.2.4
(WR)	Water resistance (Water absorption)	N/A	≤ 3 cm ²	6.2.5
(M)	Metatarsal protection	N/A	≥ 40 mm	6.2.6

Upper				
Component	Description	Value	Norm Requirements	EN 20345
Nabutek	Tear resistance	190 N	≥ 120 N	5.4.3
	Traction resistance	N/A	≥ 15 N/mm ²	5.4.4
	Water steam permeability	1,8 mg/cm ² h	≥ 0.8 mg/cm ² h	5.4.6
	pH value	4,35	≥ 3,2	5.4.7
	Chromium VI	Not detected	Not detectable	5.4.9
	Water passed	0 g	≤ 0.2 g	6.3
	Water absorption	12%	≤ 30%	6.3

Lining				
Component	Description	Value	Norm Requirements	EN ISO 20345
3D hi-tech	Tear resistance	30 N	≥ 15 N	5.5.1
	Abrasion resistance	• Dry : the surface shows no holes	No holes till 51.200 cycles	5.5.2
Fabric		• humid: the surface shows no holes	No holes till 25.600 cycles	5.5.2
	Water steam release	7,2 mg/cm ² h	≥ 2,0 mg/cm ² h	5.5.3
	pH value	N/A	Not detectable	5.5.4
	Chromium VI	N/A	Not detectable	5.5.5

Insole				
Component	Description	Value	Norm Requirements	EN ISO 20345
Fresh'nFlex	Thickness	3,5 mm	≥ 2,0 mm	5.7.1
	pH value	N/A	Not detectable	5.7.2
	Water absorption	109 mg/cm ²	≥ 70 mg/cm ²	5.7.3
	Water release	100 %	≥ 80 %	5.7.3
	Abrasion resistance (after 400 cycles)	No damage	Damage ≤ to norms reference	5.7.4.1
	Chromium VI	N/A	Not detectable	5.7.5

Removable footbed				
Component	Description	Value	Norm Requirements	EN ISO 20345
Dry n' air gel	Thickness	3,5±0,5 mm	N/A	5.7.1
	pH value	N/A	Not detectable	5.7.2
	Water absorption	Permeable	Permeable or ≥ 70mg/cm ²	5.7.3
	Water release	Permeable	Permeable or ≥ 80%	5.7.3
	Abrasion resistance	No damage	Dry No holes till 25600 cycles Humid no holes till 12800 cycles	5.7.4.2
	Chromium VI	N/A	Not detectable	5.7.5

Sole				
Component	Description	Value	Norm Requirements	EN ISO 20345
PU Midsole Air Tech Outsole TPU SKIN: (TPU high density)	Sole thickness without profiles	4,5mm	≥ 4 mm	5.8.1.1
	Profile height	3 mm	≥ 2,5 mm	5.8.1.3
	Tear resistance	6,2 kN/m	≥ 5 kN/m	5.8.2
	Abrasion resistance	141 mm ³	≤ 250 mm ³	5.8.3
	• relative volume loss			
	Flexion resistance	2,5 mm	≤ 4 mm	5.8.4
	• Notches increase after 30.000 cycles			
	Notches increase after 150.00 cycles	1 mm	≤ 6 mm	5.8.5
	Tread- Midsole detachment	N/A	≥ 4 N/mm; (*) ≥ 3 N/mm with sole ripping	5.8.6
	(HRO) Contact heat resistance (300°C)	N/A	No damage (melting, breaking)	6.4.1
(FO) Fuel resistance (volume changes)	-0,2 %	≤ 12%	6.4.2	

Date: 02/04/2013

Issued by: Responsible technician Eng. A. DITERLIZZI

Signature

